



HUNTER
CONTINUOUS INSULATION

Hunter Panels Xci CG (Class A)


Polyisocyanurate Insulation Manufactured On-Line to Coated Glass Facers with a Class A Foam Core for Exterior Commercial Wall Applications

Xci CG (Class A) Thermal Values

Thickness (inches)	Thickness (mm)	R-Value
1.0	25	6.0
1.5	38	9.0
2.0	51	12.1
2.5	64	15.3
3.0	76	18.5
3.5	89	21.7
4.0	102	25.0

Initial thermal values as per ASTM C 518 in accordance with ASTM C 1289.

HUNTER PANELS Xci CG (CLASS A)



* The location and number of WRBs in the wall assembly are determined by the architect. Contact Hunter Panels for a list of approved WRBs for each assembly.

Description

Xci CG (Class A) is an energy efficient rigid insulation panel composed of a closed cell Class A polyisocyanurate foam core manufactured on-line to premium performance coated glass facers on both sides. It is designed for use in commercial wall applications to provide continuous insulation within the building envelope.

Premium Performance Attributes

- Polyiso offers increased R-value per inch vs mineral fiber, XPS or EPS options
- Designed for use in continuous insulation to assist in meeting the most current ASHRAE 90.1, IECC, IBC and IRC standards
- Manufactured with NexGen Chemistry: Zero Ozone Depleting Potential (ODP); Contains no CFCs, HCFCs or HFCs; Virtually zero Global Warming Potential (GWP). Use of Xci products helps reduce the carbon footprint of buildings.
- Can be installed directly on steel studs in a variety of wall assemblies without the need for gypsum sheathing
- Flame Spread of <25 per ASTM E 84
- Provides R-values from 6.0–25.0 in a single layer
- Superior fire performance, durability, dimensional stability, and resistance to mold growth

Applications

- Provides continuous insulation (ci) for standard wood frame, FRT wood frame, steel stud, CMU and concrete exterior wall constructions
- Compatible with numerous claddings/finishes including masonry, fiber cement, stucco, terra cotta, mcm, metal, natural stone, stone aluminum
- Underslab, below-grade and sandwich panel applications

Note: Xci CG (Class A) is not suitable for exposed interior applications.

Panel Characteristics

- ASTM C 1289 Type II, Class 2, Grade 3 (25 psi)
- Available in 4' x 8' (1220mm x 2440mm) panels in thickness of 1" (25mm) – 4" (102mm)
- Other widths/lengths are available upon special request – (for example: 16" or 24" width)

Codes and Compliances

- ASTM C 1289
- IBC Chapter 26 and IRC Section R316
- Numerous NFPA 285 compliant assemblies
- Numerous UL 263 hourly designs
- DRJ Technical Evaluation Report 1402-01
- California Code of Regulations, Title 24, Insulation Quality Standard License #TI-1420
- California Bureau of Furnishings and Home Insulation
- CCMC 13460-L Type 3, Class 2
- CAN/ULC S-704 Type 2, Class 2

LEED Potential credits for Polyiso use

Energy and Atmosphere

- Optimize Energy Performance

Materials & Resources

- Building Life-Cycle Impact Reduction
- Environment Product Declaration
- Material Reuse
- 9% Pre-consumer Recycled Content
- Construction and Demolition Waste Management

Indoor Environmental Quality

- Thermal Comfort


Hunter Panels Xci CG (Class A)

Polyisocyanurate Insulation Manufactured On-Line to Coated Glass Facers with a Class A Foam Core for Exterior Commercial Wall Applications

Typical Physical Property Data Chart

Property	Test Method	Value
Compressive Strength	ASTM D 1621	25 psi min (172 kPa, Grade 3)
Dimensional Stability	ASTM D 2126	2% linear change (7 days)
Moisture Vapor Permeance	ASTM E 96	<1.2 perm (63.2ng/(Pa•s•m ²))
Air Permeance	ASTM E 2178	<0.001 L(s•m ²) at 75 Pa
Impact Resistance (Janka Ball Test)	ASTM D 1037	15
Water Absorption	ASTM C 209	< 0.1% volume
Service Temperature		-100° to 250° F (-73°C to 122°C)
Resistance to Mold	ASTM D 3273	Passed (10)
Flame Spread Index (foam core)	ASTM E 84	< 25
Smoke Developed (foam core)	ASTM E 84	< 250
Recycled Content		9% pre-consumer

HUNTER PANELS Xci CG (CLASS A)



* Contact Hunter Panels for a list of approved WRBs and a complete list of assemblies where gypsum is not required.

Installation

- Xci CG (Class A) is not a structural sheathing; exterior cladding must be attached through to the framing
- Always follow local codes for structural bracing
- Refer to local codes and practices for placement of the WRB in the wall assembly
- Follow cladding manufacturer's recommendation for attachment requirements
- Insulation installation may require separate fasteners or adhesives depending on the exterior cladding attachment
- Adhesives can be used for attachment to CMU, gypsum and concrete
- Metal furring strips can be installed on the exterior, fastened through the insulation to the structural wall to create a drainage plane
- Xci CG (Class A) is compatible with most construction grade adhesives, sealants, caulks, tapes, and spray foams

Post-Installation Exposure

During the time frame between installation of Xci CG (Class A) and the application of the finished exterior cladding, it is recommended that a building wrap be applied to the Xci CG (Class A). If a building wrap has not been specified, ALL UNFACED FOAM EXPOSED TO DIRECT DAYLIGHT (i.e. corners, window and door openings) should be taped with a compatible waterproof tape. Xci CG (Class A) is not intended to be left exposed for extended periods of time (i.e. in excess of 60 days) without adequate protection. Please contact Hunter Panels for details.

WRB

The incorporation of Weather Resistant Barriers (air, vapor and moisture) is a critical element of a wall assembly. A design professional familiar with local code requirements should specify the selection and placement of any WRB. Furthermore, it is recommended that a hygrothermal analysis of the proposed assembly be conducted to determine the type and location of a proposed WRB.

Note: The NFPA 285 fire test is an assembly test. The performance of the WRB must also be considered. Please consult Hunter Panels for details and specifications.

Job-Site Storage

Good construction practice dictates that all insulations should be protected from moisture and direct sunlight during job-site storage. Pallets of Hunter Panels Xci CG (Class A) are double packaged in a UV resistant polyethylene bag. This moisture resistant package is designed for protection from the elements during flat bed shipment from our factories to the job-site. Outdoor storage for extended periods of time requires waterproof tarpaulins and elevated storage above ground level a minimum of 2". Additionally, we recommend slitting the bundle packaging vertically down the center of the two short sides to prevent moisture accumulation within the package.

Warnings and Limitations

Insulation must be protected from open flame. Hunter Panels will not be responsible for specific building design by others, for deficiencies in construction or workmanship, for dangerous conditions on the job site or for improper storage and handling. Technical specifications shown in this literature are intended to be used as general guidelines only and are subject to change without notice. Call Hunter Panels for more specific details.



Hunter Panels | Energy Smart Polyiso | 888.746.1114 | www.hunterpanels.com

New York Illinois Florida Texas Utah Pennsylvania Washington



HUNTER
CONTINUOUS INSULATION